

EcoBoard Black

Chipboard with a deep black offset paper on front and grey back



GRAMMAGE	THICKNESS	BULK
g/m ²	µm	cm ³ /g
500	700	1.40
600	810	1.35
700	940	1.34
800	1150	1.44
900	1300	1.45
1000	1350	1.35
1100	1500	1.36
1200	1700	1.42
1300	1750	1.35
1400	1890	1.35
1500	2030	1.35
1600	2160	1.35
1700	2300	1.35
1800	2440	1.36
1900	2580	1.36
2000	2720	1.36



APPLICATIONS

Graphics • POS displays • folding cartons • presentation folders • decoration

PRINTING

Offset printing • flexographic printing • screen printing

CONVERSION

UV, water-based and conventional varnish • foil and film lamination • hot foil stamping and cold foil transfer • embossing (high, relief, structure, micro) • die cutting, creasing, grooving, perforating, flock coating

ADDITIONAL INFORMATION

www.kapag.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	± 5%
Thickness (DIN EN 20534)	± 5%
Bulk	± 5%
Stiffness (DIN 53121).....	
Brightness (ISO 2470)	
Opacity (ISO 2471)	
Roughness (ISO 8791/4)	

Printing Surface Properties

ISO Brightness	
Roughness	
Opacity	



The mark of responsible forestry
FSC® C058892