

# EcoBoard White

Laminated chipboard with wood-free, white offset paper on front and grey back



GRAMMAGE	THICKNESS	BULK
g/m <sup>2</sup>	µm	cm <sup>3</sup> /g
500	750	1.50
600	800	1.33
700	1000	1.43
800	1100	1.38
900	1350	1.50
1000	1400	1.40
1100	1500	1.36
1200	1700	1.42
1300	1800	1.38
1400	1900	1.36
1500	2100	1.40
1600	2200	1.38
1700	2300	1.35
1800	2450	1.36
1900	2600	1.37
2000	2750	1.38



## APPLICATIONS

Graphics • POS displays • folding cartons

## PRINTING

Offset printing • flexographic printing • screen printing

## CONVERSION

UV, water-based and conventional varnish • foil and film lamination • hot foil stamping and cold foil transfer • embossing (high, relief, structure, micro) • die cutting, creasing, grooving, perforating, flock coating

## ADDITIONAL INFORMATION

[www.kapag.com](http://www.kapag.com)

### Tolerances / Testing Standards

Grammage (DIN ISO 536) .....	± 5%
Thickness (DIN EN 20534) .....	± 5%
Bulk .....	± 5%
Stiffness (DIN 53121) .....	
Brightness (ISO 2470) .....	± 2 Elrepho (front side)
Opacity (ISO 2471) .....	
Roughness (ISO 8791/4) .....	

### Printing Surface Properties

ISO Brightness (front side).....	103%
Roughness .....	
Opacity .....	



The mark of responsible forestry  
FSC® C058892