


Alpha WhiteCore

Paperboard for museum purposes with white front and reverse side; acid free, buffered and wood free

GRAMMAGE	THICKNESS	BULK
g/m ²	µm	cm ³ /g
360	500	1.39
740	1000	1.35
1100	1500	1.36
1500	2000	1.33
1850	2500	1.35



APPLICATIONS

Mounting board for picture framing • luxury packaging • archive boxes for museum and archiving purposes

PRINTING

Offset printing • flexo printing • screen printing

CONVERSION

UV, water-based and conventional varnish • foil and film lamination • hot foil stamping and cold foil transfer • embossing (high, relief, structure, micro) • die cutting, creasing, grooving, perforating, flock coating

ADDITIONAL INFORMATION

Brochure *The KAPAG collection*, Page 8 • www.kapag.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	± 5%
Thickness (DIN EN 20534)	± 5%
Bulk	± 5%
Stiffness (DIN 53121)	
Brightness (ISO 2470)	
Opacity (ISO 2471)	
Roughness (ISO 8791/4)	

Printing Surface Properties

ISO Brightness	
Roughness	
Opacity	

Aging Resistance (Archiving Standards)

ISO 9706	
ISO 16245 Type A (except for <i>Light White</i> and <i>Hellweiss</i>).....	



The mark of
responsible forestry
FSC® C058892