

## EcoBoard GK1 machine-finished front

Chipboard with machine-finished front and light grey front and back, can be die-cut and grooved

GRAMMAGE	THICKNESS	BULK	BENDING STIFFNESS	
g/m <sup>2</sup>	µm	cm <sup>3</sup> /g	MD Nxmm	CD Nxmm
300	450	1.50	31	9
350	480	1.37	31	9
400	550	1.38	80	22
450	650	1.44	92	25
500	700	1.40	113	31
550	770	1.40	127	38
600	850	1.42	202	60
650	920	1.42	247	94
700	1040	1.49	282	122
750	1060	1.41	296	131
800	1110	1.39	337	150



### APPLICATIONS

- Sleeve boxes • folding cartons
- calendar backing • POS displays

### PRINTING

- Offset printing • screen printing

### CONVERSION

- Die cutting, creasing, grooving

### ADDITIONAL INFORMATION

- Brochure *The KAPAG collection*, Page 14 • [www.kapag.com](http://www.kapag.com)

#### Tolerances

Grammage (DIN ISO 536) .....	±7%
Thickness (DIN EN 20534) .....	±7%
Bulk .....	±7%
Stiffness (DIN 53121).....	-15%
Brightness (ISO 2470) .....	
Opacity (ISO 2471) .....	
Roughness (ISO 8791/4) .....	

#### Printing Surface Properties

ISO Brightness .....	
Roughness .....	
Opacity .....	

#### Aging Resistance (Archiving Standards)

ISO 9706 .....	
ISO 16245 Type B .....	

