

EcoDesign Duo Screen with grey middle layer

Laminated solid bleached board, double coated on both sides; recycled middle layer



GRAMMAGE	THICKNESS	BULK
g/m ²	µm	cm ³ /g
800	1000	1.25
1170	1500	1.28
1585	2000	1.26
1885	2500	1.33
2300	3000	1.30



APPLICATIONS

Graphics • POS displays • folding cartons

PRINTING

Screen printing

CONVERSION

UV, water-based and conventional varnish • foil and film lamination • hot foil stamping and cold foil transfer • embossing (high, relief, structure, micro) • die cutting, creasing, grooving, perforating, flock coating

ADDITIONAL INFORMATION

www.kapag.com

Tolerances / Testing Standards

Print Surface Properties

Grammage (DIN ISO 536)	± 5%
Thickness (DIN EN 20534)	± 5%
Bulk	± 5%
Stiffness (DIN 53121)	
Brightness (ISO 2470)	± 2.5 Elrepho (front and reverse side)
Opacity (ISO 2471)	± 2%
Roughness (ISO 8791/4)	± 0.6

ISO Brightness (front and reverse side).....	101.5%
Roughness	1.5 µm
Opacity	100.0%



The mark of
responsible forestry
www.fsc.org

GZGK.EDx2
January 2015