

EcoWoodBoard

Wood pulp board with yellowish front and back side



GRAMMAGE	THICKNESS	BULK
g/m ²	µm	cm ³ /g
360	750	2.08
500	1000	2.00
750	1500	2.00
1010	2000	1.98
1300	2500	1.92
1540	3000	1.95
1790	3500	1.96
2080	4000	1.92
2600	5000	1.92



APPLICATIONS

Calendar backing • POS displays

PRINTING

Flexo printing • screen printing

CONVERSION

Lamination

ADDITIONAL INFORMATION

www.kapag.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	±5%
Thickness (DIN EN 20534)	±5%
Bulk	±5%
Stiffness (DIN 53121)	
Brightness (ISO 2470)	
Opacity (ISO 2471)	
Roughness (ISO 8791/4)	

Printing Surface Properties

ISO Brightness	
Roughness	
Opacity	

pH value

ISO 6588	7.5 - 10.0 (acid free)
----------------	------------------------



The mark of
responsible forestry
FSC® C058892