

EcoWoodBoard self-adhesive

Wood pulp board with self-adhesive front side and coated folding box board on back side



| GRAMMAGE | THICKNESS | BULK |
|------------------|-----------|--------------------|
| g/m ² | µm | cm ³ /g |
| 650 | 800 | 1.23 |
| 740 | 1000 | 1.35 |
| 900 | 1400 | 1.56 |
| 930 | 1500 | 1.61 |
| 950 | 1600 | 1.68 |
| 1100 | 1800 | 1.64 |
| 1250 | 2000 | 1.67 |
| 1550 | 2500 | 1.61 |



APPLICATIONS

Photos • posters • crafts

PRINTING

Flexo printing • screen printing

CONVERSION

Die cutting

ADDITIONAL INFORMATION

www.kapag.com

Tolerances / Testing Standards

| | |
|--------------------------------|-----|
| Grammage (DIN ISO 536) | ±5% |
| Thickness (DIN EN 20534) | ±5% |
| Bulk | ±5% |
| Stiffness (DIN 53121) | |
| Brightness (ISO 2470) | |
| Opacity (ISO 2471) | |
| Roughness (ISO 8791/4) | |

Printing Surface Properties

| | |
|----------------------|--|
| ISO Brightness | |
| Roughness | |
| Opacity | |

pH value

| | |
|----------------|------------------------|
| ISO 6588 | 7.5 - 10.0 (acid free) |
|----------------|------------------------|



The mark of
responsible forestry
FSC® C058892

SELF.EWB3

January 2020 (replaces September 2014)